

Technical Data Sheet

E-ins Ice9™ Flex

Thermally conductive, electrically insulating plastic
Product code: TCEI-TPE3-240-000

Product type: filament or pellets
Properties based on 3D printed samples



GENERAL PROPERTIES	VALUE			
Base Material	Thermoplastic elastomer (TPE)			
Color	White			
Density	1500 kg/m ³			
THERMAL PROPERTIES	METRIC	ENGLISH		ASTM
Thermal conductivity, in-plane	4 W/m-K	27	BTU·in/hr·ft ² ·°F	E1461
Thermal conductivity, through-plane	1.5 W/m-K	10	BTU·in/hr·ft ² ·°F	E1461
Coefficient of thermal expansion	80 ppm/°C	44	ppm/°F	E831
Heat deflection temperature, 0.45 MPa	80 °C	176	°F	D648
Max. continuous temperature	120 °C	248	°F	*
MECHANICAL PROPERTIES	METRIC	ENGLISH		ASTM
Shore Hardness	95 A			D2240
Tensile modulus	210 MPa	34	ksi	D638
Tensile strength, Break	12 MPa	2	ksi	D638
Elongation at break	15 %	15	%	D638
Impact strength, Izod notched	No break	No break		D256
ELECTRICAL PROPERTIES	METRIC	ENGLISH		ASTM
Volume resistivity	>10 ¹⁴ Ω·cm			D257
FDM PRINTING GUIDELINES	METRIC	ENGLISH		
Extruder temperature	230-250 °C	445-480	°F	
Bed temperature	40-90 °C	105-195	°F	

* Max. continuous temperature is the highest temperature recommended for operation of more than 1 hour and is based internal testing and not any recognized standard.

DISCLAIMER: This material is a proprietary composition of TCPoly, Inc. U.S. and international patents pending. The testing and product data provided in this data sheet are preliminary in nature accurate. The data contained herein are provided for preliminary informational purposes only and for initial evaluation of the product. As a result, they are not appropriate for the purpose of developing a final specification and should not be relied on for such specification purposes. TCPoly extends no warranties, makes no representations and assumes no responsibility as to the accuracy or suitability of this information or this product for any purchaser's or user's use or for any consequence of its use. TCPoly disclaims any warranty of merchantability or warranty of fitness for any particular use. All statements, technical information and recommendations contained herein are based on seller's or manufacturer's tests and the tests of others. Judgment as to the suitability of information herein for the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for the intended application.

Recommended FDM Print Settings

E-ins Ice9™ Flex

Thermally conductive, electrically insulating plastic
Product code: TCEI-TPE3-240-000

Product type: FDM filament



GENERAL PROPERTIES

Base material	Thermoplastic elastomer (TPE)
Color	White
Filament diameter	1.75 or 2.85 +/- 0.05 mm

TEMPERATURE SETTINGS

	VALUE	UNITS
Extruder temperature	230-250	°C
Bed temperature	40-90	°C
Cooling fan	Off	

SLICING SETTINGS

	VALUE	UNITS
Print speed	< 30	mm/s
Layer height	>0.2	mm
Retraction distance	4-8	mm
Infill for best thermal performance	100	%

ADDITIONAL GUIDELINES

Nozzle diameter	>0.4 mm
Extruder type (1.75 mm)	Direct only
Extruder type (2.85 mm)	Direct or Bowden
Print bed preparation	Painter's tape
Storage instructions	Sealed bag
Drying instructions	2 hr @ 70°C

DISCLAIMER: This material is a proprietary composition of TCPoly, Inc. U.S. and international patents pending. The testing and product data provided in this data sheet are preliminary in nature accurate. The data contained herein are provided for preliminary informational purposes only and for initial evaluation of the product. As a result, they are not appropriate for the purpose of developing a final specification and should not be relied on for such specification purposes. TCPoly extends no warranties, makes no representations and assumes no responsibility as to the accuracy or suitability of this information or this product for any purchaser's or user's use or for any consequence of its use. TCPoly disclaims any warranty of merchantability or warranty of fitness for any particular use. All statements, technical information and recommendations contained herein are based on seller's or manufacturer's tests and the tests of others. Judgment as to the suitability of information herein for the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for the intended application.