

Technical Data Sheet

Ice9™ Rigid

Thermally conductive, electrically non-insulating nylon plastic
Product code: TC-PA-130-000

Product type: filament or pellets
Properties based on 3D printed samples



GENERAL PROPERTIES	VALUE
Base Material	Nylon
Color	Dark gray
Density	1450 kg/m ³

THERMAL PROPERTIES	METRIC	ENGLISH	ASTM
Thermal conductivity, in-plane	4 W/m-K	28 BTU·in/hr·ft ² ·°F	E1461
Thermal conductivity, through-plane	1 W/m-K	7 BTU·in/hr·ft ² ·°F	E1461
Specific heat	1100 J/kg-K	0.31 BTU/lb·°F	E1269
Coefficient of thermal expansion	60 ppm/°C	33 ppm/°F	E831
Heat deflection temperature, 0.45 MPa	175 °C	347 °F	D648
Max. continuous temperature	200 °C	392 °F	*

MECHANICAL PROPERTIES	METRIC	ENGLISH	ASTM
Shore Hardness	70 D		D2240
Flexural modulus	4 GPa	580 ksi	D638
Tensile strength, Break	30 MPa	16 ksi	D638
Elongation at break	1 %	1 %	D638
Impact strength, Izod notched	50 J/m	1 lb-ft/in	D256

ELECTRICAL PROPERTIES	METRIC	ASTM
Volume resistivity	10 ⁶ Ω-cm	D257

* Highest temperature recommended for operation of more than 1 hour and is based internal testing and not any recognized standard.

DISCLAIMER: This material is a proprietary composition of TCPoly, Inc. U.S. and international patents pending. The testing and product data provided in this data sheet are preliminary in nature accurate. The data contained herein are provided for preliminary informational purposes only and for initial evaluation of the product. As a result, they are not appropriate for the purpose of developing a final specification and should not be relied on for such specification purposes. TCPoly extends no warranties, makes no representations and assumes no responsibility as to the accuracy or suitability of this information or this product for any purchaser's or user's use or for any consequence of its use. TCPoly disclaims any warranty of merchantability or warranty of fitness for any particular use. All statements, technical information and recommendations contained herein are based on seller's or manufacturer's tests and the tests of others. Judgment as to the suitability of information herein for the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for the intended application.

Recommended FDM Print Settings

Ice9™ Rigid

Thermally conductive, electrically non-insulating nylon plastic
Product code: TC-PA-130-000

Product type: FDM filament



GENERAL PROPERTIES

Base material	Nylon
Color	Dark gray
Filament diameter	1.75 or 2.85 +/- 0.05 mm

TEMPERATURE SETTINGS

	VALUE	UNITS
Extruder temperature	265-290	°C
Bed temperature	70-80	°C
Chamber temperature	60-70	°C
Cooling fan	60%, Bridging Only	

SLICING SETTINGS

	VALUE	UNITS
Print speed	30-50	mm/s
Layer	0.15-0.6	mm
Retraction distance	5-8	mm
Retraction Speed	40-50	mm/s
Coasting distance	0-0.3	mm
Infill for best thermal performance	95-100	%

ADDITIONAL GUIDELINES

Nozzle diameter	0.3-1.0 mm
Extruder type (1.75 mm)	Direct or Bowden
Extruder type (2.85 mm)	Direct or Bowden
Print bed preparation	Glue stick on PEI or Glass
Drying instructions	4 hr @ 80°C
Storage instructions	Sealed bag
Part removal from bed	Heat bed to 100°C then gently remove with spatula